



Pressure Pad Material

1/8" RUBBER MATTING

6510
 For: General membrane protection purposes

Classification		
	Properties	
ASTM D3676 Density pcf	40 min	
Specific Gravity		
ASTM D412 Tensile, psi	75 min	
% Elongation	60 min	
ASTM F-36 % Compressibility		Recovery
100 psi	25-35	85 min
200 psi	40-50	85 min
300 psi	50-60	85 min
400 psi	60-70	85 min
ASTM D2240 Shore A2	20-60	
ASTM D624 Die C Tear PPI	20 min	
ASTM F147 flexibility Factor	1	
ASTM D395 Compression Set B		
25% deflection, 158 degrees/22 hrs	20-30	
ASTM D3676 Compression (Foam)		
50% deflection, 158 degrees/22 hrs	20-30	

Loose gravel must always be removed from area where rubber matting will be installed.

The values shown represent current production and may vary under different conditions.